



**RAMPF**<sup>®</sup>



**ESTERLÖSSL GMBH**  
COMPOSITE-TECHNOLOGIE + WERKSTOFFE

## Expandierendes Epoxy System: EC 2401 / EH 2904 / EPC 50 Treibmittel

EC 2401	100	100	100
EH 2904	15	15	15
EP 50	1	2	3
Foaming Volume	225%	275%	375%
Tg °C			
Dichte	0,53 g/cm <sup>3</sup>	0,35 g/cm <sup>3</sup>	0,28 g/cm <sup>3</sup>

EC 2401	100	100	100
EH 2904	20	20	20
EP 50	1	2	3
Foaming Volume	250%	325%	400%
Tg °C			
Dichte	0,44 g/cm <sup>3</sup>	0,31 g/cm <sup>3</sup>	0,24 g/cm <sup>3</sup>

EC 2401	100	100	100
EH 2904	25	25	25
EP 50	1	2	3
Foaming Volume	275%	375%	475%
Tg °C			
Dichte	0,42 g/cm <sup>3</sup>	0,26 g/cm <sup>3</sup>	0,20 g/cm <sup>3</sup>

