



# RAMPF®



## ESTERLÖSSL GMBH

COMPOSITE-TECHNOLOGIE + WERKSTOFFE

Polyurethan Giesssysteme <b>RAKUTOOL</b>			Farbe	Kombination	Mischungsverhältnis	Topfzeit Min	max. Schichtdicke (mm)	Shore-Härte ISO 868	Bruchdehnung %
Poly	Poly	Iso							
PC 3451		PH 3952	elfenbein	A	100 : 60	20	20	D 65	100 - 120
PC 3451	PH 3911	PH 3952	caramel	B	100 : 24 : 56	35	30	D 40	150 - 200
PC 3451	PH 3911	PH 3952	caramel	C	100 : 45 : 55	40	40	D 35	200 - 250
PC 3451	PH 3911	PH 3952	caramel	D	100 : 105 : 45	50	50	A 85	250 - 300
	PC 3411	PH 3911	schwarz	E	10 : 100	50	80	A 80	750 - 780
PC 3410	PC 3411	PH 3911	schwarz	F	25 : 7,5 : 150	60	75	A 65	680 - 730
PC 3410	PC 3411	PH 3911	schwarz	G	50 : 5 : 200	60	90	A 55	600
PC 3410	PC 3411	PH 3911	schwarz	H	75 : 2,5 : 250	60	100	A 50	600
PC 3410		PH 3911	schwarz	I	100 : 300	60	100	A 40	600

**Shore A - D Härte ist über das Mischungsverhältnis einstellbar**

