

**RAMPF****ESTERLÖSSL GMBH**  
COMPOSITE-TECHNOLOGIE + WERKSTOFFE

<b>Blockmaterial RAKU TOOL®</b>	Anwendung	Dichte (g/cm <sup>3</sup> )	Wärmeform- beständigkeit ISO 75 (°)	Wärme- ausdehnungs- koeffizient	Druckfestigkeit ISO 604 (Mpa)	Dimension (mm)
<b>WB 0690</b>	Epoxyboard für Prepreg	0,7	95	35	50 - 55	1500 x 500 x 50 1500 x 500 x 75 1500 x 500 x 100 1500 x 500 x 150 1500 x 500 x 200
<b>WB 0700</b>	Epoxyboard für Prepreg	0,75	135	35	50 - 55	1500 x 500 x 50 1500 x 500 x 75 1500 x 500 x 100 1500 x 500 x 150 1500 x 500 x 200
<b>WB 1210</b>	Gießerei- Serieneinrichtung	1,20	90 - 95	50 - 60	110	1000 x 500 x 50 1000 x 500 x 75 1000 x 500 x 100
<b>WB 1222</b>	Gießerei- modellbau kleine bis mittlere Serien	1,22	80 - 90	85 - 90	60 - 70	1000 x 500 x 50 1000 x 500 x 75 1000 x 500 x 100
<b>WB 1250</b>		1,25	80-75	70-75	70 - 80	1000 x 500 x 50 1000 x 500 x 75 1000 x 500 x 100
<b>WB 1404</b>		1,40	80 - 90	50-55	85 - 90	1000 x 500 x 50 1000 x 500 x 75 1000 x 500 x 100
<b>WB 1450</b>		1,45	75 - 80	65 - 75	70 - 75	1000 x 500 x 50 1000 x 500 x 75 1000 x 500 x 100
<b>WB 1000</b>	Lehren, Werkzeuge	1,10	60 - 70	50 - 55	55 - 60	1500 x 500 x 50 1500 x 500 x 75 1500 x 500 x 100
<b>WB 1440</b>	Klopfmodelle und Bördelwerkzeuge	1,50	80 - 85	60 - 65	80 - 85	1000 x 500 x 50 1000 x 500 x 100
<b>WB 1600</b>	Metallumform- werkzeuge Lehren	1,60	75 -80	45 - 50	90 - 100	750 x 500 x 50 750 x 500 x 75 750 x 500 x 100
<b>WB 1700</b>	RTM -Formen Druckgußformen	1,7	120 - 125	45 - 50	125 - 130	750 x 500 x 50 750 x 500 x 75 750 x 500 x 100

